



## DEL-VAL BLIND NAILING CEMENT

### Description and Specs:

Del-Val Blind Nailing Cement is manufactured by blending specialty asphalts, mineral fillers and safe quick flash solvents. This enables the product to set more quickly with less slippage of field sheets. Del-Val Blind Nailing Cement is formulated to a heavy brush consistency thus providing a secure bed in which to lay sheet goods. Meets ASTM D-3019 Type III. **(Asbestos Free Cement)**

### Uses:

Del-Val Blind Nailing Cement is most frequently used in the application of 90 lb. or SIS Felt roofing as a cold process adhesive. It can also be used, with polyester mat, as an inter-ply, cold process adhesive in the creation of a BUR system. In some instances Del-Val Blind Nailing Cement is used over older BUR roofs as a flood coat prior to the introduction of aggregate or other protective coating.

### Method and Rate of Application:

Apply to a dry, dirt and oil free surface with a brush, roller, spray gun or serrated trowel. If being applied to an aggregate roof, all loose aggregate should be removed. Any repairs should be made using Del-Val Flashing Cement and United Asphalt Fabric. If adhering 90 lb. or SIS Felts, 1.5 to 2 gallons of material per 100 sq. ft. should be used. Take notice there is a 1/8 in. to 1/4 in. bleed-out along seams. If used in a cold applied BUR system 2 to 4 gallons per 100 sq. ft. is recommended. Drying time is 8 to 24 hours depending on thickness and weather conditions.

### Safety:

**CAUTION! COMBUSTIBLE!** KEEP OUT OF REACH OF CHILDREN. Keep away from heat and flame. Do not heat container or store at temperatures greater than 110° F. Avoid breathing fumes and prolonged contact with skin.

**DANGER! HARMFUL OR FATAL IF SWALLOWED!** If **swallowed**, do not induce vomiting. CALL A PHYSICIAN IMMEDIATELY! When cleaning up, dispose of cans, rags and trowels in accordance with local laws. Keep container closed when not in use to avoid spills.

### Container Sizes:

5 gallon	42 lbs.
55 gallon	480 lbs.

### Clean-up:

Remove product from tools, etc., with kerosene or mineral spirits. Clean hands with a waterless hand cleaner.

United Asphalt Company  
237 North Grove Street Williamstown Junction, NJ 08009  
PO Box 291 Cedar Brook NJ  
856-753-9811 • 800-843-0317 • FX: 856-753-9809  
[www.unitedasphalt.com](http://www.unitedasphalt.com)