

The logo for United Asphalt, Co. features the word "United" in white text inside a black oval, followed by "Asphalt, Co." in orange text.

Quality Products Since 1963

UNITED DAMP-MASTIC TROWEL GRADE "DAMPPROOFING"

Description and Specs:

United Damp –Mastic Trowel Grade is a **SOLVENT BASED** blend of select refined asphalts mineral fibers, and waterproofing gums. The formulation of these materials in exact proportions creates heavily bodied trowel grade cement. Used in conjunction with United Damp –Mastic Brush Grade to secure a tight seal against moisture. When dry, it is very flexible and protects very well against certain natural chemicals found in soil. Meets ASTM D-4586 Type I. (**Asbestos Free Cement**)

Uses:

United Damp –Mastic Trowel Grade is used in conjunction with United Damp-Mastic Brush Grade, to dampproof masonry and concrete walls below grade.

Method and Rate of Application:

Apply with a contractor's trowel. Make sure that the area that is going to be covered is done so in an evenly consistent application. Apply at the rate of 5-6 gallons per 100 square feet. Please allow the mastic at least 36 hours before backfilling. This gives the mastic time for curing.

Safety:

CAUTION! COMBUSTIBLE! KEEP OUT OF REACH OF CHILDREN. Keep away from heat and flame. Do not heat container or store at temperatures greater the 110° F. Avoid breathing fumes and prolonged contact with skin.

DANGER! HARMFUL OR FATAL IF SWALLOWED! If **swallowed**, do not induce vomiting. CALL A PHYSICIAN IMMEDIATELY! When cleaning up, dispose of cans, rags and trowels in accordance with local laws. Keep container closed when not in use to avoid spills.

Container Sizes:

5 gallon 56 lbs.

Clean-up:

Remove product from tools, etc., with kerosene or mineral spirits. Clean hands with a waterless hand cleaner.

United Asphalt Company
237 North Grove Street Williamstown Junction, NJ 08009
PO Box 291 Cedar Brook NJ
856-753-9811 • 800-843-0317 • FX: 856-753-9809
www.unitedasphalt.com