



UNITED ASPHALT FIBERED EMULSION

Description and Specs:

United Asphalt Fibered Emulsion is a blend of choice refined asphalts, emulsifiers and reinforcing fibers dispersed in water with the aid of colloidal clay. This product, when dry, cures to a tough protective barrier that resists alligatoring, cracking and blistering. United Fibered Emulsion is designed for challenging applications where a solvent based primer coat is not desired. This product is also compatible with an EPS board. Meets ASTM D-1227 Type IV. **(Asbestos Free)**

Uses:

United Fibered Emulsion can be used as a coating for resurfacing asphalt and composition roofs or as the adhesive in a cold applied BUR system. This product is often used with EPS boards either below grade or on a roof surface. United Asphalt Emulsion can also be used as a primer coat prior to the application of United Aluminum Coatings.

Method and Rate of Application:

Apply with a brush, roller or spray gun to a surface that is free of dirt, dust and any loose particles. The surface may be primed (metal surfaces must be primed) with any United Asphalt Primer. Stir before and during usage to ensure a uniform coating throughout application. Spread emulsion over a preferably damp roof surface. Apply at a rate of 4 gallons per 100 sq. ft. for a flood coat or 2 to 3 gallons per 100 sq. ft. for a cold applied BUR system, making sure fabric being used is completely embedded in coating. Drying time is approximately 24 to 72 hours. Do not over coat with aluminum for at least 5 days. Use only when temperature is 50 degrees and rising and there is no chance of freezing until cure has been attained. Do not use if rain is imminent. Do not thin product.

Safety:

CAUTION! COMBUSTIBLE! KEEP OUT OF REACH OF CHILDREN. Keep away from heat and flame. Do not heat container or store at temperatures greater than 110° F. Avoid breathing fumes and prolonged contact with skin.

DANGER! HARMFUL OR FATAL IF SWALLOWED! If swallowed, do not induce vomiting. CALL A PHYSICIAN IMMEDIATELY! When cleaning up, dispose of cans, rags and trowels in accordance with local laws. Keep container closed when not in use to avoid spills.

Container Sizes:

5 gallon	43 lbs.
55 gallon	480 lbs.

Clean-up:

Remove product from tools, etc., with kerosene or mineral spirits, if material is wet use water otherwise. Clean hands with a waterless hand cleaner.

United Asphalt Company
237 North Grove Street Williamstown Junction, NJ 08009
PO Box 291 Cedar Brook NJ
856-753-9811 • 800-843-0317 • FX: 856-753-9809
www.unitedasphalt.com